

Taktika B

Primer before painting

- Evens out the absorption
- Facilitates painting, repairing of defects in the smoothed surface before painting
- Reduces paint consumption
- Forms a deep matt film
- Water-based
- Water vapor permeable
- Environment and health friendly

USE

Water-based acrylic copolymer primer before painting for interior use.

Evens the absorption of mineral surfaces (concrete, plaster, putty, masonry, gypsum boards, painted wallpaper, etc.) before painting with water-based dispersion paint.

SURFACE PREPARATION

The surface must be stable, dry and clean. Sand the filled surface and remove the dust.

APPLICATION

Stir well before use. Using a roller, apply one coat of primer in the same direction and roll well to a smooth surface (without texture). If you apply the primer with a sprayer, after spraying, roll it well with a roller.

Work tools: brush, roller, spraying gun

Tool cleaning: with water

Application conditions: +10 °C to +25 °C and 35–80 % relative humidity. Avoid drafts and direct sunlight during priming. Failure to follow these recommendations, may form poor-quality primer film.

Coverage rate: 8–10 m²/l, applied in 1 layer. The exact coverage rate is determined by covering the test area.

Drying time (23 °C, 50 % RH): completely dries in 24 hours. Drying time depends on surface, layer thickness, air temperature, humidity, etc.

WASTE MANAGEMENT

Do not pour into drains, water or soil. Empty, dry product package should be recycled or disposed of in accordance with national law.



TECHNICAL DATA

Purpose:	for interior use
Binder:	acrylic copolymer
Solvent:	water
Color:	white or tinted by color cards
Density:	1,230–1,250 g/cm ³
pH:	8,0–9,0
Volatile organic compounds (VOC):	<15 g/l EN ISO 11890-2
Non-volatile-matter content by volume:	21,0–24,0 % LST EN ISO 3251
Classification by maximum grain size:	fine (to 100 µm) EN 13300+AC
Degree of gloss, 85°:	<5 (dead matt) EN 13300+AC
Resistance to static water (40±2 °C, 24 h):	after 24 hours defect rating 0 (S0) EN ISO 2812-2; EN ISO 4628-1
Shelf life in tightly closed original packaging:	24 months from the date of manufacture
Storage and transportation conditions:	store the product tightly closed in dry well-ventilated place at a temperature of +5 °C to +30 °C, protect against from damage, frost and direct sunlight.
Packing:	Taktika B 1 l; 3 l; 10 l buckets

ADDITIONAL INFORMATION

The information above is based on laboratory tests and practical experience, and has been validated from the date indicated on the product data sheet. The manufacturer reserves the right to make technical changes. The manufacturer is not liable for damage caused by using the product not in accordance with the instructions or for improper purposes.

MANUFACTURER

Sole Proprietorship of I. Krisciunas "IGIS", Tinklu str. 33-1, Panevezys, Lithuania
+370 684 72323
www.igis.lt

